



## TUBES FROM COLD ROLLED MATERIAL TUBI DA NASTRO LAMINATO A FREDDO

Weight and availability table / *Pesi e gamma produttiva*

Ø OD Ø Esterno mm	OD Tolerances* Tolleranza	Theoretic weight kg / m - <i>Pesi teorici kg / m</i>						
		Nominal thickness mm - <i>Spessori nominali mm</i>						
		1,00	1,20	OD Tolerances* Tolleranza	1,50	2,00	2,50	3,00
40,0		0,98	1,18		1,47	1,96		
42,0		1,03	1,23		1,54	2,06		
50,0		1,22	1,47		1,84	2,45		
50,8		1,24	1,49		1,87	2,49		
54,0		1,32	1,59		1,98	2,65		
58,0		1,42	1,70		2,13	2,84		
60,0		1,47	1,76		2,20	2,94		
63,0		1,54	1,85		2,31	3,09		
65,0		1,59	1,91		2,39	3,18		
70,0		1,71	2,06		2,57	3,43		
73,0		1,79	2,15		2,68	3,58		
<b>74,0</b>		<b>1,81</b>	2,17		2,72	3,62		
75,0		1,84	2,20		2,76	3,67		
<b>76,2</b>		1,87	2,24		<b>2,80</b>	3,73		
<b>80,0</b>		<b>1,96</b>	<b>2,35</b>		<b>2,94</b>	3,92		
82,0		2,01	2,41		3,01	4,02		
85,0		2,08	2,50		3,12	4,16		
89,0		2,18	2,62		3,27	4,36		
90,0		2,20	2,65		3,31	4,41		
94,0		2,30	2,76		3,45	4,60		
95,0		2,33	2,79		3,49	4,65		
<b>100,0</b>		2,45	<b>2,94</b>		3,67	<b>4,90</b>		
<b>101,6</b>		<b>2,49</b>	2,99		3,73	4,98		
103,0		2,52	3,03		3,78	5,05		
104,0		2,55	3,06		3,82	5,09		
<b>105,0</b>		2,57	<b>3,09</b>		3,86	5,14		
106,0		2,60	3,12		3,89	5,19		
<b>108,0</b>		2,65	3,17		3,97	<b>5,29</b>		
110,0		2,69	3,23		4,04	5,39		
<b>114,3</b>		2,80	3,36		4,20	<b>5,60</b>		
115,0		2,82	3,38		4,22	5,63		
118,0		2,89	3,47		4,34	5,78		
<b>120,0</b>		<b>2,94</b>	<b>3,53</b>		4,41	5,88		
<b>122,0</b>	+/-1%	<b>2,99</b>	3,59	+/-0,5%	4,48	5,98		
123,0		3,01	3,62		4,52	6,03		
124,0		3,04	3,64		4,56	6,07	7,59	9,11
125,0		3,06	3,67		4,59	6,12	7,65	9,18
127,0		3,11	3,73		4,67	6,22	7,78	9,33
129,0		3,16	3,79		4,74	6,32	7,90	9,48
130,0		3,18	3,82		4,78	6,37	7,96	9,55
132,0		3,23	3,88		4,85	6,47	8,08	9,70
133,0		3,26	3,91		4,89	6,51	8,14	9,77
134,0		3,28	3,94		4,92	6,56	8,20	9,85
136,0		3,33	4,00		5,00	6,66	8,33	9,99
<b>138,0</b>		<b>3,38</b>	4,06		5,07	6,76	8,45	10,14
139,0		3,40	4,09		5,11	6,81	8,51	10,21
140,0		3,43	4,11		5,14	6,86	8,57	10,29
143,0		3,50	4,20		5,25	7,00	8,76	10,51
<b>145,0</b>		3,55	4,26		5,33	7,10	8,88	10,65
<b>150,0</b>		3,67	<b>4,41</b>		5,51	7,35	9,18	11,02
152,0		<b>3,72</b>	4,47		5,58	7,45	9,31	11,17
153,0		3,75	4,50		5,62	7,49	9,37	11,24
154,0		3,77	4,53		5,66	7,54	9,43	11,32
155,0		3,80	4,56		5,69	7,59	9,49	11,39
159,0		3,89	4,67		5,84	7,79	9,74	11,68
160,0		3,92	4,70		5,88	7,84	9,80	11,76
161,0		3,94	4,73		5,91	7,89	9,86	11,83
163,0		3,99	4,79		5,99	7,98	9,98	11,98
165,0		4,04	4,85		6,06	8,08	10,10	12,12
170,0		4,16	5,00		6,25	8,33	10,41	12,49
<b>177,0</b>		<b>4,34</b>	5,20		6,50	8,67	10,84	13,01
178,0		4,36	5,23		6,54	8,72	10,90	13,08
179,0		4,38	5,26		6,58	8,77	10,96	13,15
180,0		4,41	5,29		6,61	8,82	11,02	13,23
184,0		4,51	5,41		6,76	9,01	11,27	13,52
194,0		4,75	5,70		7,13	9,50	11,88	14,25
195,0		4,78	5,73		7,16	9,55	11,94	14,33
<b>200,0</b>		4,90	<b>5,88</b>		7,35	9,80	12,25	14,70
<b>202,0</b>		<b>4,95</b>	5,94		7,42	9,89	12,37	14,84

\* The diameter has to be measured at 150mm from the edge.

*Il diametro deve essere misurato a 150 mm dalla estremità.*

Usually available also from cold-rolled strip EK for enamelling.  
*Generalmente disponibili anche da nastro a freddo EK per smaltatura.*

Usually available also from cold-rolled strip DC01.  
*Generalmente disponibili anche da nastro a freddo DC01.*

Usually available also from cold-rolled strip DC04.  
*Generalmente disponibili anche da nastro a freddo DC04.*

Ø OD	OD Tolerances* Tolleranza	1,50	2,00	2,50	3,00
203,0		7,46	9,94	12,43	14,92
204,0		7,49	9,99	12,49	14,99
206,0		7,57	10,09	12,61	15,14
<b>220,0</b>		8,08	10,78	13,47	<b>16,16</b>
250,0		9,18	12,25	15,31	18,37
252,0	+/-1%	9,26	12,34	15,43	18,52
253,0		9,29	12,39	15,49	18,59
254,0		9,33	12,44	15,55	18,66
300,0		11,02	14,70	18,37	22,04
304,0		11,17	14,89	18,61	22,34